

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B23K 35/363, 35/36 // 101:42	A1	(11) International Publication Number: WO 96/37336 (43) International Publication Date: 28 November 1996 (28.11.96)
(21) International Application Number: PCT/US96/07705 (22) International Filing Date: 24 May 1996 (24.05.96) (30) Priority Data: 08/448,683 24 May 1995 (24.05.95) US (71) Applicant: FRY'S METALS INC. [US/US]; 600 Route 440, Jersey City, NJ 07304 (US). (72) Inventor: DIEP-QUANG, Hiep; Apartment 3404, 30 Newport Parkway, Jersey City, NJ 07310 (US). (74) Agent: MIRABITO, A., Jason; Wolf, Greenfield & Sacks, P.C., 600 Atlantic Avenue, Boston, MA 02210 (US).		(81) Designated States: CA, JP, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: EPOXY-BASED, VOC-FREE SOLDERING FLUX (57) Abstract A resin-based VOC-free soldering flux consists of 40 to 50 wt.% of a liquid epoxy resin, 25 to 30 wt.% of a non-volatile liquid epoxy diluent, 20 to 33 wt.% of a polyfunctional carboxylic acid, and 2.0 to 3.5 wt.% of a thixotropic agent. There are no volatile organic solvents or compounds in the flux which can evaporate during the reflow process. The carboxylic acids are provided in powdered form and are suspended in the epoxy blend wherein they remain as solid particles until heated in the solder reflow process. A VOC-free solder paste formed from the flux consists of 40 to 95 wt.% soldering particles, and 5 to 60 wt.% of the VOC-free soldering flux. The thixotropic agent improves printability of the solder paste onto printed wiring boards. A VOC-free flux-core solder wire includes the VOC-free flux as the inner core of the wire with an outer shell of solder alloy. The VOC-free, epoxy resin based flux effectively activates the solder powder and the copper contact during the reflow process, while at the same time hardens to leave a solid, dry, yet flexible residue on a printed wiring board. No organic compounds are emitted during the reflow process.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Larvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

EPOXY-BASED, VOC-FREE SOLDERING FLUX**Background and Summary of the Invention**

5 The instant invention relates to soldering fluxes and solder pastes, and more particularly to an epoxy-based soldering flux which does not contain any volatile organic compounds or solvents (VOC's).

Soldering fluxes and solder pastes have heretofore been known in the art. In this regard, 10 solder pastes are used to connect the leads of electronic elements to contact pads on a printed wiring board (PWB). In use, solder pastes are printed onto the copper contact pads of PWB, the leads of the electronic element are placed in proper position on top of the PWB contact pads, and then the entire PWB assembly is heated to achieve reflow of the solder paste to form a connection between the leads of the electronic element and the contact pads of the PWB.

15 Solder paste, in general, comprises a homogenized mixture of solder powder and a soldering flux which, when mixed with the solder powder, gives the mixture the physical characteristics of a paste. The soldering flux is typically a solution of a resin, usually a rosin or rosin derivative, and an organic acid activator dissolved in a volatile organic solvent. The organic solvent typically comprises up to 80 wt% (percent by weight) of the flux composition. 20 The organic acid activator in the soldering flux actively removes an oxide film from the metallic components when applied to the metal surfaces thereof, thus allowing the melted solder to flow freely over and bind to all fluxed surfaces. Thixotropic agents and other viscosity modifiers can also be present to achieve the desired rheological characteristics of the soldering flux and/or solder paste.

25 During the reflow, i.e. heating, process, most of the organic solvent evaporates into the air leaving a solid residue on the PWB. Furthermore, besides the evaporation of the organic solvents, a significant amount additional of organic material becomes airborne as fume through decomposition or sublimation of the solid residue. While the prior art solder pastes and fluxes have been highly effective for their intended purposes, the evaporation of the organic solvent and 30 release of organic materials during solder reflow pose many problems which have recently become a significant concern in the industry. Firstly, volatile organic compounds (VOC's) and VOC emissions are now receiving stricter scrutiny from an environmental perspective. More

stringent environmental regulations are requiring the reduction of organic emissions in all industrial application. Secondly, VOC emissions are a burden to the reflow equipment in that the VOC's recondense onto the cold parts of the equipment, corroding metal, causing electrical failure, and clogging ventilation ducts. Another disadvantage to organic solvent based solder pastes is that in the case of rosin type pastes, the solid residue is brittle, and prone to cracking. Many manufacturers of printed wiring boards are now producing flexible circuit structures, i.e. flexi-circuits, and the brittleness and cracking of solvent based solder pastes is unacceptable in these types of applications. The use of plasticizers to remedy the brittleness of rosin-type organic solvent solder pastes makes the organic residue sticky, and unsuitable for pin-testing of the PWB after reflow.

The instant invention provides an epoxy-based, VOC-free soldering flux comprising 40 to 50 wt% (percent by weight) of epoxy resin, 25 to 30 wt% of non-volatile liquid epoxy diluent, 20 to 33 wt% of an activating agent which is insoluble, i.e. unreactive, in the epoxy system at room temperature, and 2.0 to 3.5 wt% of a thixotropic agent. In the instant soldering flux, the activating agent also serves as a curing agent for the epoxy resin system. There are no organic solvents in the soldering flux which can evaporate during the reflow process. The epoxy diluent can be either a reactive diluent containing one or more epoxy functional groups, such as polyglycol diepoxide, or a non-reactive diluent, such as a polyether diol. More specifically, the soldering flux preferably comprises 40 to 50 wt% of bisphenol A type epoxy resin, 25 to 35 wt% polyglycol diepoxide (epoxy diluent), 20 to 35 wt% of a polyfunctional carboxylic acid (activating agent and curing agent), such as malic acid, and 2.0 to 3.5 wt% of hydrogenated castor oil (thixotropic agent).

The instant invention further provides a VOC-free solder paste formed from the above-described flux consisting of 40 to 95 wt% soldering particles, and 5 to 60 wt% of the above-described VOC-free soldering flux. The soldering particles preferably comprise 63Sn/37Pb alloy solder particles having mesh size of about 325 to 500. The thixotropic agent added to the flux composition improves printability of the solder paste onto printed wiring boards. The activating agent of the flux effectively activates the solder powder and the copper contact during the reflow process, while at the same time cures the epoxy so that it hardens to leave a solid, dry, yet flexible residue on a printed wiring board. The activating/curing agent is selected so that its melts just prior to the reflow process so that activation, curing of the resin, and reflow of the solder particles occur almost simultaneously.

The instant invention still further provides a flux-core solder wire formed from the above-described VOC-free soldering flux. The flux-core solder wire is formed according to conventional solder wire forming techniques resulting in a wire structure having an inner core of the instant VOC-free soldering flux, and an outer shell of a solder alloy.

5 Accordingly, among the objects of the instant invention are the provision of an epoxy-based VOC-free soldering flux which hardens after the reflow process to form a solid, dry, flexible residue on the printed wiring board; the provision of a VOC-free solder paste; and the provision of a VOC-free flux-core solder wire.

Other objects, features and advantages of the invention shall become apparent as the
10 description thereof proceeds herein.

Description of the Preferred Embodiments

SOLDERING FLUX

15 As will hereinafter be more fully described, the instant soldering flux is based on an epoxy resin system, wherein there are no volatile organic solvents or compounds present.

The instant VOC-free soldering flux consists essentially of an activating agent, an epoxy curing agent, and a thixotropic agent blended in a mixture of a reactive epoxy resin and a non-volatile liquid epoxy diluent. No organic solvents are present in the instant soldering flux. In the
20 instant invention, it is preferred that the activating agent also acts as the curing agent for the epoxy resin.

The reactive epoxy resin comprises the primary ingredient in the instant soldering flux consisting of about 40% to about 50% by weight of the entire flux composition. In the instant invention, reactive epoxy resins having at least two reactive epoxy groups are particularly
25 preferred. In this connection, bisphenol A type resin has been found to be particularly suitable for the instant flux composition, although other resins having similar characteristics are also suitable. For example, epoxy novolac resins and polyglycol epoxy resins are also suitable.

Most of the above-noted epoxy resins have a viscosity (around 100 Poise) which is too high for effective use in a printable soldering flux or solder paste. According to the instant
30 invention, the epoxy resin is blended with low molecular weight, low viscosity, non-volatile liquid epoxy diluent having a viscosity around 5 Poise to achieve a lower viscosity solution. A viscosity in the range of about 10 Poise to about 50 poise (25°C, Brookfield) is particularly

preferred for the instant soldering flux. In this regard, the non-volatile diluent preferably comprises about 25% to about 30% by weight of the entire flux composition. The epoxy diluent may comprise a reactive diluent containing one or more reactive epoxy groups, for example a low molecular weight polyol, such as polyglycol diepoxide, or an oligomer having at least one epoxy group per molecule. Other suitable reactive diluents include alkyl glycidyl ethers, and glycidyl acid esters.

Furthermore, the epoxy diluent may alternatively comprise a non-reactive diluent, for example a polyether diol with a molecular weight under 1000. However, other non-reactive diluents which are also effective include nonyl phenol, furfuryl alcohol, and dibutyl phthalate.

The blend of epoxy resin and epoxy diluent is called the epoxy resin system which comprises between about 75% to about 80% by weight of the entire soldering flux.

To further improve printability of the flux composition, a thixotropic agent, for example, hydrogenated castor oil, is preferably added to the resin system. Other suitable thixotropic agents include polyamides, and polyethylene waxes. The thixotropic agent preferably comprises about 2.5% to about 3.5% by weight of the entire flux composition.

The activating agent comprises an organic acid, preferably a polyfunctional carboxylic acid, such as malic acid, glutaric acid, succinic acid, or azelaic acid, or citric acid. A polyfunctional carboxylic acid has more than one carboxylic acid group, which means that this category comprises the dicarboxylic acids (2 carboxylic acid groups) like malic acid, glutaric acid, succinic acid, and azelaic acid, and tricarboxylic acids (3 carboxylic groups) like citric acids. All of these acids are suitable for use in soldering fluxes. The carboxylic acid may further comprise a linear dicarboxylic acid having the following general structure:



wherein $n = 2$ to 5 .

An additional requirement of the activating agent is that it must remain in solid, i.e. unreactive form, at room temperature. There should be no reaction at all between the dispersed activating/curing agent and the epoxy resin at room temperature. The activating/curing agent must therefore be insoluble in the resin system. In this regard, the activating agents are provided in a powdered form and blended into the epoxy resin system wherein they remain suspended in powdered form until the soldering flux is heated. In this manner, the activation/curing reaction

can start only after the activating/curing agent has been melted. It is pointed out that the particular epoxy resin and activating/curing agent selected are determined by the melting temperature of the solder/solder alloy to be used. The reaction starting temperature of the epoxy resin with the activating agent must be slightly lower than the melting point of the solder. For example, the reflow temperature of Sn63/Pb37 solder alloy is about 183°C. Therefore, activating agents having a melting temperature of about 130 to 180°C can be considered. An activating/curing agent with a lower melting temperature would initiate the curing reaction too far ahead of the reflow process, while an activating agent with a higher melting temperature would start the reaction too late, resulting in the reflow process being completed before the resin system can be fully cured.

In the instant invention, it is preferred that the activating agent also act as the curing agent for the epoxy resin system. In this regard, the polyfunctional carboxylic acids described hereinabove have been found to be suitable both as an activating agent and as a curing agent. In the alternative, additional curing agents, such as triisopropanolamine, can be added to the soldering flux to catalyze the curing process. Other curing agents which are suitable include melamine, 2-amino pyrimidine, and 2, 4, 6-triamino pyrimidine.

The curing reaction rate of the curing agent with the epoxy resin system is a function of the number of reaction sites, i.e. functional epoxy groups, available, expressed in wt% epoxide. The standard epoxy resins described above, including bisphenol A type resin, each have a wt% epoxide of about 25. The low viscosity epoxy diluent, i.e. polyglycol diepoxide, has a wt% epoxide of about 7. Non-reactive epoxy diluents have a 0 wt% epoxide. It has been found that the resin blend must preferably have an overall wt% epoxide of about 15 to about 20, and more preferably of about 17 wt% epoxide, for the flux to work properly, i.e. to result in a dry, non-sticky, flexible residue after curing.

EXAMPLES

Flux Preparation #1

40 wt% bisphenol A type resin (molecular weight 378) (epoxide equivalent weight 189) was blended with 25 wt% polyether diol (molecular weight 760) resulting in a low viscosity epoxy resin system. 3.5 wt% hydrogenated castor oil was dispersed in the epoxy resin system at 75°C for 15 minutes. The blend was cooled down to 40°C and 26 wt% malic acid (fine powdered form) and 0.5 wt% triisopropanolamine (fine powdered form) were dispersed in the

blend under high shear.

Flux Preparation #2

Prepared as in flux 1 using 50 wt% bisphenol type A epoxy resin, 25 wt% polyglycol
5 diepoxide (viscosity 30-60 centipoise), 2.0 wt% hydrogenated castor oil, 20 wt% glutaric acid,
and 3 wt% malic acid.

Flux Preparation #3

Prepared as in flux 2 using 50 wt% bisphenol A type epoxy resin, 25 wt% polyglycol
10 diepoxide (viscosity 30-60 centipoise), 2 wt% hydrogenated castor oil, 20 wt% succinic acid, and
3.0 wt% malic acid.

Flux Preparation #4

Prepared as in flux 2 using 50 wt% bisphenol A type epoxy resin, 25 wt% polyglycol
15 diepoxide, 2 wt% hydrogenated castor oil, 20 wt% azelaic acid, and 3.0 wt% malic acid.

SOLDER PASTE

A solder paste in accordance with the instant invention comprises about 40 to about 95
wt% of powdered soldering particles and about 5 to about 60 wt% VOC-free soldering flux as
20 described herein. The soldering particles preferably comprise tin-lead alloys, such as Sn63/Pb37
having a reflow temperature of about 183°C, and alternatively can comprise silver-tin-lead
alloys, bismuth-tin-lead alloys, gold-tin-lead alloys, or iridium-tin-lead alloys. The soldering
particles preferably have a mesh size of about 325 to about 500, although other size soldering
particles are also suitable depending upon the particular application of the solder paste.

25

EXAMPLE

SOLDER PASTE PREPARATION

130 g of soldering flux as prepared in flux preparation 2 is mixed with 870 g of solder
powder Sn63/Pb37, 325-500 mesh to yield about 1kg of solder paste.

30

In use, the solder paste is printed onto a printed wiring board (PWB) according to
conventional printing techniques, an electronic package is placed in position over the printed

areas of the PWB, and the PWB is placed in a solder reflow oven. The oven is raised to the solder reflow temperature in a typical spike curve as is well known in the art. As the temperature rises above the melting temperature of the activating agent, the activating agent melts and activates the solder and copper contact pads to remove any oxide film on the surfaces thereof.

- 5 The activating agent further acts as a curing agent to begin coupling reactions of the epoxy system. When the temperature rises to the solder reflow temperature, the solder melts and reflows over the surfaces to effect a solder bond between the copper land, and the leads of the electronic package, while the epoxy system is simultaneously cured. When the reflow process is complete, the epoxy based flux dries to leave a clear, flexible residue, which does not lose any of
10 its volume. Since there are no organic solvents or compounds, no organic materials are released into the air. The flexible, dry residue does not require cleaning, and acts as a mechanical reinforcement between the electronic package and the PWB, making the application particularly suitable for flexi-circuits. Since the residue is non-sticky, it is also particularly suitable for pin testing of the soldering joints after reflow.

15

FLUX-CORE SOLDER WIRE

- The instant VOC-free flux composition is also effective for use in a flux-core solder wire. Flux-core solder wires are typically used in manual soldering procedures wherein the solder wire is melted via a hand-held soldering iron. One problem in the industry with regard to prior art
20 flux-core solder wires is the direct exposure of employees working with soldering irons to the toxic VOC emissions released from the rosin-based solder fluxes during manual soldering operations.

- A flux-core solder wire in accordance with the instant invention comprises a wire structure having an inner core of the above-described VOC-free soldering flux, and an outer shell
25 of a solder alloy as previously described. For example, the solder alloy preferably comprises a tin-lead alloy, such as Sn63/Pb37, which has a reflow temperature of about 183°C, and alternatively can comprise silver-tin-lead alloys, bismuth-tin-lead alloys, gold-tin-lead alloys, or iridium-tin-lead alloys. Core solder wires and their manufacture have heretofore been known in the art, and therefore, the specific means of manufacture will not be further described herein.

30

EXAMPLE

VOC-FREE FLUX-CORE SOLDER WIRE

Soldering flux as prepared in flux preparation 1 (above) is co-extruded with solder alloy Sn63/Pb37 according to conventional manufacturing techniques to yield flux-core solder wire
5 having the described solder flux as the central core thereof.

It is still further contemplated that the instant VOC-free flux composition will be utilized as an underfill material in a Direct Chip Attach Package.

It can therefore be seen that the instant invention provides an effective, and environmentally friendly, VOC-free soldering flux, VOC-free solder paste, and VOC-free flux-
10 core solder wire. The soldering flux is composed of up to 80 wt% epoxy resin system, whereas the prior art solvent based soldering fluxes comprised up to 80 wt% organic solvent. The activating/curing agent is suspended in the epoxy resin as a fine solid particle, and becomes active only after melting in the reflow process, whereas in the prior art soldering fluxes, the activating agents are dissolved in the solvent and are thus active at room temperature. The
15 instant VOC-free soldering flux does not lose any weight after reflow heating. The epoxy system of the flux cures to leave a clear, solid, flexible residue which acts as a mechanical reinforcement between the electronic package and the PWB, whereas in the prior art soldering fluxes, the organic solvent evaporated to lose up to 80 wt% leaving a brittle residue. For these reasons, the instant invention is believed to represent a significant advancement in the art which has substantial
20 commercial merit.

While there is shown and described herein certain specific structure embodying the invention, it will be manifest to those skilled in the art that various modifications and rearrangements of the parts may be made without departing from the spirit and scope of the underlying inventive concept and that the same is not limited to the particular forms herein
25 shown and described except insofar as indicated by the scope of the appended claims.

Claims:

1. A VOC-free soldering flux comprising:

a reactive epoxy resin;
a non-volatile liquid epoxy diluent;
a soldering activating agent;
an epoxy curing agent; and
a thixotropic agent.

2. The VOC-free soldering flux of claim 1, wherein said reactive epoxy resin has a polymer chain including at least two reactive epoxy groups.

3. The VOC-free soldering flux composition of claim 1, wherein said non-volatile liquid epoxy diluent comprises an oligomer having at least one epoxy group per molecule.

4. The VOC-free solder flux composition of claim 1, wherein said non-volatile liquid epoxy diluent comprises a low molecular weight polyol.

5. The VOC-free solder flux composition of claim 4, wherein said non-volatile liquid epoxy diluent comprises polyglycol diepoxide.

6. The VOC-free solder flux composition of claim 1, wherein said soldering activating agent comprises an organic acid.

7. The VOC-free solder flux composition of claim 6, wherein said epoxy curing agent comprises said organic acid.

8. The VOC-free solder flux composition of claim 7, wherein said organic acid comprises a polyfunctional carboxylic acid.

9. The VOC-free solder flux composition of claim 7, wherein said organic acid comprises a linear dicarboxylic acid having the following chemical structure:



wherein $n = 2$ to 5 .

5

10. A VOC-free solder paste comprising:

a VOC-free solder flux composition including a reactive epoxy resin, a non-volatile liquid epoxy diluent, a soldering activating agent, an epoxy curing agent, and a thixotropic agent; and

10 soldering particles.

11. The VOC-free solder paste of claim 10 wherein said soldering particles comprise between about 40% to about 95% by weight of said solder past and said VOC-free solder flux composition comprises between about 5% to about 60% by weight of said solder paste.

15

12. The solder paste of claim 10 wherein said soldering particles are selected from the group consisting of: tin-lead alloys, silver-tin-lead alloys, bismuth-tin-lead alloys, gold-tin-lead alloys, and iridium-tin-lead alloys.

20 13. A VOC-free solder flux compsoiton comprising:

between about 40% to about 50% by weight of a reactive epoxy resin;

between about 25% to about 30% by weight of a non-volatile liquid epoxy diluent; and

25 between about 20% to about 35% by weight of a soldering activating agent, said activating agent also functioning as a curing agent for said epoxy resin.

14. The VOC-free solder flux composition of claim 13, wherein said epoxy resin has a polymer chain including at least two epoxy groups.

30 15. The VOC-free solder flux composition of claim 14, wherein said epoxy resin comprises bisphenol A type epoxy resin.

16. The VOC-free solder flux composition of claim 13, wherein said liquid epoxy diluent comprises an oligomer having at least one epoxy group per molecule.

17. The VOC-free solder flux composition of claim 16, wherein said liquid epoxy diluent
5 comprises a polyol.

18. The VOC-free solder flux composition of claim 17, wherein said liquid epoxy diluent comprises polyglycol diepoxide.

10 19. The VOC-free solder flux composition of claim 13, wherein said activating agent comprises a polyfunctional carboxylic acid.

20. The VOC-free solder flux composition of claim 19, wherein said carboxylic acid comprises malic acid.

15 21. The VOC-free solder flux composition of claim 20, wherein said carboxylic acid comprises a linear dicarboxylic acid having the general structure:



wherein $n = 2$ to 5 .

20 22. The VOC-free solder flux composition of claim 13 further comprising a thixotropic agent.

23. The VOC-free flux composition of claim 22, wherein said thixotropic agent comprises
25 hydrogenated castor oil.

24. The VOC-free flux composition of claim 22, wherein said thixotropic agent comprises between about 2% to about 3.5% by weight of said flux composition.

25. A VOC-free solder pasted comprising:

a VOC-free solder flux composition including between about 40% to about 50% by weight of a reactive epoxy resin, between about 25% to about 30% by weight of a non-volatile liquid epoxy diluent, and between about 20% to about 35% by weight of a soldering
5 activating agent; and
soldering particles.

26. The VOC-free solder paste of claim 25, wherein said soldering particles comprise between about 40% to about 95% by weight of said solder paste and said flux composition
10 comprises between about 5% to about 60% by weight of said solder paste.

27. The solder paste of claim 20 wherein said soldering particles are selected from the group consisting of: tin-lead alloys, silver-tin-lead alloys, bismuth-tin-lead alloys, gold-tin-lead alloys, and iridium-tin-lead alloys.

15

28. A VOC-free flux-core solder wire construction comprising:

an inner core of a VOC-free soldering flux; and
an outer shell of a solder alloy, said VOC-free soldering flux comprising a reactive epoxy resin, a non-volatile liquid epoxy diluent, a soldering activating agent, an epoxy
20 curing agent, and a thixotropic agent.